



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) **EP 1 297 973 A1**

(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:
02.04.2003 Bulletin 2003/14

(51) Int Cl.7: **B60C 1/00**, B60C 11/14,
B60C 11/00

(21) Application number: **02021550.5**

(22) Date of filing: **26.09.2002**

(84) Designated Contracting States:
**AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
IE IT LI LU MC NL PT SE SK TR**
Designated Extension States:
AL LT LV MK RO SI

- **Uchida, Mamoru,**
Sumitomo Rubber Industries, Ltd.
Kobe-shi, Hyogo-ken (JP)
- **Ota, Takeshi, Sumitomo Rubber Industries, Ltd.**
Kobe-shi, Hyogo-ken (JP)

(30) Priority: **27.09.2001 JP 2001296925**

(71) Applicant: **Sumitomo Rubber Industries Ltd.**
Kobe-shi, Hyogo-ken (JP)

(74) Representative:
Manitz, Finsterwald & Partner GbR
Postfach 31 02 20
80102 München (DE)

(72) Inventors:
• **Minagoshi, Akira,**
Sumitomo Rubber Industries, Ltd.
Kobe-shi, Hyogo-ken (JP)

(54) **Rubber composition for a tire tread and tire using the same**

(57) A rubber composition which can improve performance on icy and snowy road sufficiently and a tire using the same. The rubber composition comprises 2 to 30 parts by weight of staple fibers having an average fiber diameter of 10 to 100 μm and an average fiber length of 0.01 to 4 mm, and 1 to 10 parts by weight of particles having a Moh's hardness of at least 5 and an

average particle size of at most 500 μm based on 100 parts by weight of a diene rubber. The tire of the present invention is prepared by using the rubber composition for tread. Examples of the particle are pumice, quarts, emery and the like.

EP 1 297 973 A1

Description

[0001] The present invention relates to a rubber composition and a tire, particularly a rubber composition which can improve performances of studless tire on icy and snowy road and a tire whose tread comprises the rubber composition.

[0002] Heretofore, when automobiles are driven in cold region with heavy snowfall, studded tires or snow chain-equipped tires are used to ensure the safety on snowy and icy road. However, studded tires or chain-mounted tires easily wear out the road surface, generating dust to cause serious air pollution, which is now regarded as a significant environmental problem.

[0003] In order to guarantee safety and solve environmental issues mentioned above, studless tires which has appropriate braking and driving performances on snowy and icy road without any stud or chain has been rapidly developed.

[0004] As a studless tire, automobile tires whose performance on ice is improved by compounding sand (JP-A-61-150803) or metallic fibers (JP-A-63-34026) into the tread rubber are proposed. However, in such tires, hardness of the rubber becomes relatively high, and therefore friction on ice is insufficient. In addition, as tire wears off, those sand, metallic fibers and other metals fall off and the particles are spattered to cause a serious environmental problem of dust pollution.

[0005] Alternatively, it is also proposed to use foamed rubber for the tread rubber (JP-A-62-283001, JP-A-63-9042 and JP-A-1-118542). However, in these tires, though frictional force on ice is improved, edge effect and water discharging ability due to voids on the tread surface cannot be fully utilized because the foamed rubber has low block stiffness, and abrasion resistance and steering performance on dry road become inferior. Moreover, since foaming is performed in the vulcanization step of the production, dimensional accuracy is likely to be influenced.

[0006] In addition, techniques to compound hollow particles in the tread to improve tire performances on icy and snowy road are proposed (JP-A-11-35736 and JP-A-6-328906). However, in these tires, fine hollow particles are broken during kneading, resulting in a problem that sufficient icy and snowy road performances cannot be achieved.

[0007] For another technique, it is proposed to compound a water-absorbing synthetic polymer in the tread rubber to remove water existing between the road surface and the tread (JP-A-5-148390). However, the water absorbing ability of such synthetic polymer is insufficient, and it cannot be said that edge effect after the polymer has fallen is sufficient because the falling of the polymer does not take place immediately after the water absorption.

[0008] Other than the above, a method of improving grip performance on icy road by compounding staple fibers orientating them in the direction perpendicular to the tread face to increase digging frictional force is proposed (JP-A-2000-168315). According to these techniques, studless tires have acquired improved grip performance on icy road, but the performance is not yet comparable to that of studded tires.

[0009] An object of the present invention is to provide a rubber composition which can improve performances on icy and snowy road and a tire having those improved performances.

[0010] That is, the present invention relates to a rubber composition comprising 2 to 30 parts by weight of staple fibers having an average fiber diameter of 10 to 100 μm and an average fiber length of 0.01 to 4 mm, and 1 to 10 parts by weight of particles having a Moh's hardness of at least 5 and an average particle size of at most 500 μm based on 100 parts by weight of a diene rubber.

[0011] The present invention also relates to a tire having a tread comprising the rubber composition of Claim 1.

[0012] Examples of diene rubber used for the rubber composition of the present invention include natural rubber, isoprene rubber, butadiene rubber and styrene-butadiene rubber. These diene rubbers may be used alone or in combination of two or more.

[0013] In the rubber composition of the present invention, grip performance on icy road can be improved by compounding particular staple fibers. In particular, when the staple fibers are orientated perpendicular to the tread face, digging frictional force is further increased and therefore grip performance on icy road can be improved.

[0014] Examples of staple fibers include glass fiber, aluminum whisker, polyester fiber, nylon fiber, polyvinyl formal fiber and aromatic polyamide fiber. Among them, inorganic staple fibers having a specific gravity of at least 2.0, such as glass fiber and aluminum whisker are preferable from the viewpoint that they have excellent compatibility with rubber at kneading, achieve moderate shape after kneading and have excellent orientation.

[0015] It is preferable that the Moh's hardness of the staple fiber material is 3 to 6. When the Moh's hardness is less than 3, effect on digging friction against the icy road tends to be small. When the Moh's hardness is more than 6, there is a tendency that the surface of the staple fibers is not easily scratched by the particles as mentioned below. More preferably, the lower limit of the Moh's hardness of the staple fiber is 4 and the upper limit of the Moh's hardness of the staple fiber is 5.

[0016] The average fiber diameter of the staple fiber after dispersion in the rubber composition is 10 to 100 μm . When the average fiber diameter is less than 10 μm , flexural strength is poor and thus the digging effect remains small. When the average fiber diameter is more than 100 μm , contact area between the rubber and the ice surface is reduced and therefore adhesion effect tends to decrease. In addition, reinforcing property of the rubber is poor, so that abrasion resistance is adversely affected. Preferably, the lower limit of the average fiber diameter of the staple fiber is 15 μm ,

and the upper limit of the average fiber diameter of the staple fiber is 70 μm .

[0017] The average fiber length of the staple fiber after dispersion in the rubber composition is 0.01 to 4 mm. When the average fiber length is less than 0.01 mm, orientation tends to be difficult. When the average fiber length is more than 4 mm, viscosity of the unvulcanized rubber becomes higher and processability is decreased. Preferably, the lower limit of the average fiber length of the staple fiber is 0.3 mm and the upper limit of the average fiber length of the staple fiber is 2 mm.

[0018] The amount of staple fiber is 2 to 30 parts by weight based on 100 parts by weight of the diene rubber. When the amount of staple fiber is less than 2 parts by weight, effect on digging friction is small. When the amount of staple fiber is more than 30 parts by weight, abrasion resistance is decreased. Preferably, the lower limit of the amount of staple fiber is 4 parts by weight and the upper limit of the amount of staple fiber is 20 parts by weight.

[0019] The rubber composition of the present invention further contains particles comprising a material having a Moh's hardness of at least 5. In the step of kneading the staple fibers and the particles with the rubber, the surface of staple fibers is finely scratched owing to the friction between the particles and the staple fibers, and these scratches seem to make staple fibers not easily fall out from the base rubber. Therefore, when the Moh's hardness is less than 5, the surface of staple fiber is not easily scratched by the particles and therefore effect on digging friction is small. Preferably, the lower limit of the Moh's hardness of the material of the particle is 6 and the upper limit of the Moh's hardness of the material of the particle is 8. When the Moh's hardness is more than 8, there is a possibility that asphalt road is damaged.

[0020] The term "Moh's hardness" here means one of the mechanical characteristics of materials, which is a long-established measuring method widely used in the field of minerals. In this method, the hardness of a mineral is defined lower than that of a mineral used to scratch the former mineral when the former mineral gets scratched, in the following order of 10 minerals. In ascending order from lower hardness, 1 talc, 2 gypsum, 3 calcite, 4 fluorite, 5 apatite, 6 orthoclase, 7 crystal, 8 topaz (yellow sapphire), 9 corundum and 10 diamond are used.

[0021] Examples of materials having a Moh's hardness of at least 5 include hemimorphite, asbestos, manganese, apatite, nickel, glass, hornblende, feldspar, pumice, orthoclase, hematite, augite, iron oxide, high speed steel, tool steel, magnesia, iridium, pyrite, ruthenium, agate, chrome dioxide, garnet, steel, flint, quartz, silicon, chrome, beryllia, zirconia, iridosmium, tourmaline, andalusite, beryl, emery, osmium, topaz, tungsten carbide alloy (sintered), zirconium boride, corundum, titanium nitride, tungsten carbide, tantalum carbide, zirconium carbide, chrome, alumina (casted), alumina (a), alumina (fine crystal), silicon carbide (black), silicon carbide (green), aluminum boride, boron carbide and diamond. Among these, inorganic substances such as pumice, quartz and emery are preferable since they can give particles of desired particle size and they are relatively inexpensive. However, whether the material is organic or inorganic is not particularly limited.

[0022] The average particle size of the particle is at most 500 μm . When the average particle size is more than 500 μm , reinforcing property for the rubber is poor and abrasion resistance is adversely affected. The lower limit of the average particle size of the particle is preferably 10 μm , more preferably 30 μm , and the upper limit of the average particle size of the particle is preferably 300 μm , more preferably 150 μm . When the average particle size is less than 10 μm , the surface of the staple fiber is not easily scratched, and therefore effect on digging friction tends to be small.

[0023] The amount of the particle is 1 to 10 parts by weight based on 100 parts by weight of the diene rubber. When the amount of the particle is less than 1 part by weight, effect on digging friction is small since the surface of the staple fiber is not easily scratched. When the amount of the particle is more than 8 parts by weight, abrasion resistance is decreased.

[0024] The rubber composition of the present invention can be obtained by kneading the staple fibers and the particles with the diene rubber for 1 to 5 minutes. When the kneading time is less than 1 minute, dispersion of the staple fibers and the particles to the rubber tends to be insufficient.

[0025] In addition to the above components, the rubber composition of the present invention may be incorporated with components or additives generally used for preparing a rubber in a usual amount if necessary. Concrete examples of such components or additives include reinforcing agents (carbon black, silica); processing oils (paraffin processing oil, naphthene processing oil, aromatic processing oil); vulcanizing agents (sulfur, sulfur chloride compound, organic sulfur compound); vulcanization accelerators (guanidine, aldehyde-amine, aldehyde-ammonia, thiazole, sulfen amide, thiourea, thiuram, dithiocarbamate or xanthate compound); crosslinking agents (radical initiators such as organic peroxide compound and azo compound, oxime compound, nitroso compound and polyamine compound); antioxidants (amine derivatives such as diphenylamine and p-phenylenediamine, quinoline derivatives, hydroquinoline derivatives, monophenols, diphenols, thiobisphenols, hinderedphenols and phosphorus acid esters); waxes; stearic acids; zinc oxides; softeners; fillers; and plasticizers.

[0026] When carbon black is compounded to the rubber composition of the present invention as a reinforcing agent, it is preferable that the carbon black has a nitrogen adsorption specific surface area ($N_2\text{SA}$) of 90 to 150 m^2/g and a DBP (dibutyl phthalate) oil absorption amount of 80 to 140 $\text{ml}/100\text{ g}$.

[0027] The tire of the present invention is prepared by using the above rubber composition for the tread according

to a usual process. That is, the rubber composition is extruded and processed without vulcanization in accordance with the shape of the tread, and the composition is then formed into tread on a tire forming machine in a usual manner to obtain an unvulcanized tire. The unvulcanized tire is heated and pressurized in a vulcanizing machine to obtain a tire.

5 EXAMPLES

[0028] The present invention is explained in detail based on Examples below, but not limited thereto. "Part(s)" and "%" in the following examples mean "part(s) by weight" and "% by weight", respectively, unless otherwise specified.

[0029] Materials used in Examples and Comparative Examples are listed below. Each of emery, pumice particle A, pumice particle B and gypsum particle were prepared by pulverizing the respective bulks and sieving the pulverized substance to select particles having a specific particle size.

(Materials)

15 [0030]

Natural rubber: RSS #3

Butadiene rubber (BR): UBEPOL BR150B available from Ube Industries, Ltd.

Carbon black: SHOBLACK N220 available from Showa Cabot Co. Ltd. (N₂SA: 111 m²/g, DBP oil absorption amount: 111 ml/100 g)

Microcrystalline wax: SUN NOC N available from Ohuchi Shinko Kagaku Kogyo Co., Ltd.

Antioxidant 6PPD: NOCRAC 6C available from Ohuchi Shinko Kagaku Kogyo Co., Ltd.

Stearic Acid: Stearic acid available from NOF Corporation

Zinc oxide: Zinc Oxide available from Mitsui Mining and Smelting Co., Ltd.

Paraffin oil: Diana Process oil available from Idemitsu Kosan Co., Ltd.

Glass fiber: glass fiber available from Japan Sheet Glass Co., Ltd.

(average fiber diameter: 33 μm, average fiber length: 6 mm, Moh's hardness: 5)

Emery: prepared for this experiment (average particle size: 100 μm, Moh's hardness: 7 to 9)

Pumice particle A: prepared for this experiment (average particle size: 100 μm, Moh's hardness: 6)

Pumice particle B: prepared for this experiment (average particle size: 700 μm, Moh's hardness: 6)

Gypsum particle: prepared for this experiment (average particle size: 100 μm, Moh's hardness: 2)

Sulfur: powdery sulfur available from Tsurumi Chemicals Co., Ltd. Vulcanization Accelerator: Nocceler CZ available from Ohuchi Shinko Kagaku Kogyo Co., Ltd.

[0031] Evaluation methods in Examples and Comparative Examples are summarized below.

1. Average fiber length of glass fiber in rubber

[0032] The rubber was sintered and the glass fiber was separated from the polymer component. Thereafter, the glass fiber was observed by using a scanning electron microscope (SEM) and the average fiber length was obtained.

2. Performance on icy and snowy road

[0033] The prepared tire was mounted on a Japanese front engine/rear wheel drive automobile with an engine size of 2000 cc, and brake stopping distance was measured by stopping the automobile which was run at a speed of 30 km/h on an ice board. Evaluation was made referring to the index obtained by the following equation on the basis of the tire of Comparative Example 1. The larger the index is, the more excellent the performance on icy and snowy road is.

$$\frac{(\text{Brake stopping distance of Comparative Example 1}) + (\text{Brake stopping distance of each Example})}{\text{distance of each Example}} \times 100$$

3. Abrasion resistance

[0034] The prepared tire was mounted on a Japanese front engine/rear wheel drive automobile with an engine size of 2000 cc and run for 4,000 km to measure the groove depth of the tire tread. The driven miles at which the groove depth is decreased by 1 mm was obtained and the value was represented as an index to the value of Comparative

EP 1 297 973 A1

Example 1. The larger the index is, the better the abrasion resistance is.

(Number of driven miles at which the groove depth of each tire prepared
is decreased by 1 mm) ÷ (Number of driven miles at which the groove
depth of tire of Comparative Example 1 is decreased by 1 mm) × 100

4. Steering performance on dry road

[0035] In a dry asphalt 500-m round slalom course, running time per round was clocked and the time was represented as an index to the time of Comparative Example 1. The larger the index, the better the steering performance on dry road is.

(Running time per round of Comparative Example 1) ÷ (Running time per
round of each Example) × 100

EXAMPLES 1 and 2 and COMPARATIVE EXAMPLES 1 to 5

[0036] According to the compounds listed in Table 1, components other than sulfur and vulcanization accelerator were kneaded first. Thereafter, sulfur and vulcanization accelerator were added and further kneading was carried out. The obtained rubber composition was used for tread and a tire was prepared by a usual method. The prepared tire was subjected to the above evaluation tests. The results are shown in Table 1.

TABLE I

	Ex.					Com. Ex				
	1	2	1	2	3	4	5	1	2	3
Compound (part by weight)	70	70	70	70	70	70	70	70	70	70
Natural rubber	30	30	30	30	30	30	30	30	30	30
BR	45	45	45	45	45	45	45	45	45	45
Carbon black	2	2	2	2	2	2	2	2	2	2
Microcrystalline wax	2	2	2	2	2	2	2	2	2	2
Antioxidant	3	3	3	3	3	3	3	3	3	3
Stearic acid	5	5	5	5	5	5	5	5	5	5
Zinc oxide	15	15	15	15	15	15	15	15	15	15
Paraffin oil	10	10	10	10	10	10	10	10	10	10
Glass fiber	5	—	—	—	—	—	—	—	—	—
Emery	—	5	—	—	—	—	—	—	0.5	15
Pumice particle A	—	—	—	—	—	—	—	—	—	—
Pumice particle B	—	—	—	—	—	—	—	—	—	—
Gypsum particle	1	1	1	1	1	1	1	1	1	1
Sulfur	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5
Vulcanization accelerator	33	33	33	33	33	33	33	33	33	33
Average fiber diameter of glass fiber in rubber (μm)	0.25	0.30	0.30	0.30	0.30	0.30	0.30	0.20	0.30	0.25
Average fiber length of glass fiber in rubber (mm)	115	114	100	103	106	101	108	101	102	105
Performance on icy or snowy road	102	102	100	101	101	101	101	88	98	86
Driving performance on dry road	95	95	100	93	88	98	86	98	98	86
Abrasion resistance	95	95	100	93	88	98	86	98	98	86

[0037] In Examples 1 and 2 where glass fibers and particles having a specific Moh's hardness and particle size were compounded, performance on icy and snowy road was improved with maintaining abrasion resistance and steering performance on dry road.

[0038] On the other hand, in Comparative Example 2 where particles having a low Moh's hardness were used, effect of improving performance on icy and snowy road was small. It seems that this is because the scratching of glass fibers by particles during kneading was not enough, thus the glass fibers has fallen out from the rubber owing to running, and therefore effect on digging friction was not achieved sufficiently.

[0039] In Comparative Example 3 where particles having a large particle size was used, performance on icy and snowy road was slightly improved but abrasion resistance was remarkably decreased.

[0040] In Comparative Example 4 where only a small amount of particles was compounded, effect of compounding the particles was hardly seen.

[0041] In Comparative Example 5 where a large amount of particles was compounded, performance on icy and snowy road was improved but abrasion resistance was remarkably decreased.

[0042] According to the present invention, sufficient performance on icy and snowy road can be achieved without decreasing abrasion resistance or steering stability on dry road by using a rubber composition containing staple fibers and particular particles for tire tread.

Claims

1. A rubber composition comprising
 - 2 to 30 parts by weight of staple fibers having an average fiber diameter of 10 to 100 μm and an average fiber length of 0.01 to 4 mm, and
 - 1 to 10 parts by weight of particles having a Moh's hardness of at least 5 and an average particle size of at most 500 μm based on 100 parts by weight of a diene rubber.
2. A tire having a tread comprising the rubber composition of Claim 1.



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 02 02 1550

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
Y	EP 1 072 446 A (SUMITOMO RUBBER IND) 31 January 2001 (2001-01-31) * abstract * * paragraph [0016] * * paragraph [0021] * * paragraph [0035] - paragraph [0036] * * claim 1 *	1,2	B60C1/00 B60C11/14 B60C11/00
Y	--- PATENT ABSTRACTS OF JAPAN vol. 1996, no. 12, 26 December 1996 (1996-12-26) & JP 08 217918 A (OHTSU TIRE & RUBBER CO LTD:THE), 27 August 1996 (1996-08-27) * abstract * * paragraph [0005] - paragraph [0006] * * paragraph [0009] - paragraph [0010] *	1,2	
A	--- US 5 591 279 A (MIDORIKAWA SHINGO ET AL) 7 January 1997 (1997-01-07) * abstract * * column 1, line 41,42 * * column 2, line 13-42 * * column 3, line 11-28 * * column 3, line 39,40 * * column 3, line 62,63 * * column 4 * * column 5, line 17-19 * * claim 1 *	1,2	TECHNICAL FIELDS SEARCHED (Int.Cl.7) B60C
A	--- DE 40 05 493 A (TOYO TIRE & RUBBER CO) 23 August 1990 (1990-08-23) * page 2, line 1 * * page 2, line 22-57 * * page 3, line 27-30 * * claims 2,4 *	1,2	
-/--			
The present search report has been drawn up for all claims			
Place of search MUNICH		Date of completion of the search 25 November 2002	Examiner Thanbichler, P
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document	

EPO FORM 1503 03 02 (P04C01)



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 02 02 1550

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
A,P	EP 1 172 406 A (SUMITOMO RUBBER IND) 16 January 2002 (2002-01-16) * abstract * * paragraph [0021] - paragraph [0025] * * paragraph [0039] * * claims 1,2 * -----	1,2	
			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
The present search report has been drawn up for all claims			
Place of search MUNICH		Date of completion of the search 25 November 2002	Examiner Thanbichler, P
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

EPO FORM 1503 03.82 (P04C01)

ANNEX TO THE EUROPEAN SEARCH REPORT ON EUROPEAN PATENT APPLICATION NO.

EP 02 02 1550

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for those particulars which are merely given for the purpose of information.

25-11-2002

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 1072446 A	31-01-2001	JP 2001039104 A	13-02-2001
		EP 1072446 A2	31-01-2001
JP 08217918 A	27-08-1996	NONE	
US 5591279 A	07-01-1997	JP 6328906 A	29-11-1994
		JP 2763251 B2	11-06-1998
		JP 6328908 A	29-11-1994
		CA 2123828 A1	21-11-1994
DE 4005493 A	23-08-1990	JP 1988272 C	08-11-1995
		JP 2219836 A	03-09-1990
		JP 7002871 B	18-01-1995
		JP 1988273 C	08-11-1995
		JP 2219837 A	03-09-1990
		JP 7005800 B	25-01-1995
		JP 1988275 C	08-11-1995
		JP 2228342 A	11-09-1990
		JP 7002872 B	18-01-1995
		JP 2227303 A	10-09-1990
		DE 4005493 A1	23-08-1990
		US 5302636 A	12-04-1994
EP 1172406 A	16-01-2002	JP 2002030183 A	31-01-2002
		JP 2002047378 A	12-02-2002
		EP 1172406 A2	16-01-2002
		NO 20013436 A	15-01-2002
		US 2002026003 A1	28-02-2002

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82